

PIGMENT PERFORMANCE DATA

PRODUCT CODE	PRODUCT NAME	PIGMENT IDENTIFICATION	RESISTANCES								
			LIGHT		HEAT	SOLVENT				CHEMICAL	
			Full Shade	Tint	30 min @ °F	Aliphatic	Aromatic	Ketone	Alcohol	Acid	Base
408-34130	Zero-Verse Blue 15:2	Phthalocyanine Blue RS	5	5	390	5	5	5	5	5	5
408-34860	Zero-Verse Green 7	Phthalocyanine Green BS	5	5	390	5	5	5	5	5	5
408-35410	Zero-Verse Yellow 151	Benzimidazolone Yellow	5	4-5	390	5	4-5	4-5	4-5	5	3
408-35460	Zero-Verse Yellow Oxide	Yellow Iron Oxide	5	5	320	5	5	5	5	5	5
408-36500	Zero-Verse Red 170	Monoazo Red	4D	3	320	5	4-5	4	4-5	5	5
408-36860	Zero-Verse Red Oxide	Red Iron Oxide	5	5	390	5	5	5	5	5	5
408-37120	Zero-Verse Red 122	Quinacridone Magenta	4D	4	390	5	5	4-5	5	5	5
408-37450	Zero-Verse Violet 23	Carbazole Violet	4-5	3-4	320	5	4-5	4-5	3	5	5
408-39190	Zero-Verse Black	High Strength Carbon Black	5	5	390	5	5	5	5	5	5
408-39330	Zero-Verse Jet Black	Jet Carbon Black	5	5	390	5	5	5	5	5	5
408-39600	Zero-Verse White	Titanium Dioxide White	5	5	390	5	5	5	5	5	5

Date: 04 August 06

LEGEND:

5 – Excellent
4 – Very Good
3 – Good

2 – Fair
1 – Poor
D – Darkens