

PIGMENT PERFORMANCE DATA

PRODUCT NUMBER	PRODUCT NAME	COLOR INDEX NAME	LIGHT RESISTANCE		HEAT RESISTANCE	SOLVENT RESISTANCE				CHEMICAL RESISTANCE	
			Full Shade	Tint	30 Min @ ° F	Aliphatic	Aromatic	Ketone	Alcohol	Acid	Base
414-34100	Phthalo Blue RS	Blue 15:2	5	5	390	5	5	5	5	5	5
414-34850	Phthalo Green BS	Green 7	5	5	390	5	5	5	5	5	5
414-35411	Bright Yellow 151	Yellow 151	5	4-5	390	5	4-5	4-5	4-5	5	3
414-35471	Bright Yellow RS	Yellow 83	4D	4	390	5	3-4	3-4	4-5	5	5
414-35771	Yellow Oxide	Yellow 42	5	5	320	5	5	5	5	5	5
414-35930	Durable Orange	Orange 36	5	4-5	320	5	4-5	4-5	4-5	5	5
414-35951	Bright Orange	Orange 34	3	2	390	4-5	3	3-4	5	5	5
414-36501	Bright Red 170	Red 170	4D	3-4	320	5	4-5	4	4-5	5	5
414-36790	Red Oxide	Red 101	5	5	> 390	5	5	5	5	5	5
414-37150	Quinacridone Magenta	Red 202	4D	4-5	390	5	5	4-5	5	5	5
414-37461	Carbazole Violet	Violet 23	4-5	3-4	320	5	4-5	4	5	5	5
414-39180	Carbon Black	Black 7	5	5	>390	5	5	5	5	5	5
414-39601	TiO ₂ White	White 6	5	5	>390	5	5	5	5	5	5

Dated: 07 August 2006
Supersedes: 20 January 2003

LEGEND:

D – Darkens	3 – Good
5 – Excellent	2 – Fair
4 – Very Good	1 – Poor