



634-35660 YELLOW RS

PRODUCT 634-35660 IS A CONCENTRATED DISPERSION OF A RED SHADE MONOAZO YELLOW PIGMENT IN A SELECT LONG-OIL ALKYD RESIN IN LOW-ODOR MINERAL SPIRITS. THIS COMBINATION IS BROADLY COMPATIBLE AND FINDS USE IN THESE VEHICLES:

- OLEORESINOUS VARNISH
- LONG-OIL ALKYD
- MEDIUM-OIL ALKYD
- SHORT-OIL ALKYD
- STYRENATED ALKYD
- VINYL TOLUENATED ALKYD
- CHAIN STOPPED ALKYD
- SILICONE ALKYD
- PHENOLIC MODIFIED ALKYD
- URETHANE MODIFIED ALKYD
- EPOXY ESTERS
- NITROCELLULOSE

● = PRIMARY USE ○ = SECONDARY USE

THIS PIGMENT IS THE LARGE-CRYSTAL, OPAQUE FORM OF PIGMENT YELLOW 65. ITS VERY GOOD LIGHTFASTNESS IN MASSTONE AND TINT RECOMMEND THIS PIGMENT FOR VARIOUS AIR DRY FINISHES BASED ON MILD SOLVENT SYSTEMS. ITS HIGH CHROMA AND HIGH HIDING MAKE THE PIGMENT AN EXCELLENT COMPLEMENT TO DNA ORANGE FOR COLORMATCHING A RANGE OF BRIGHT, CLEAN SHADES. CARE MUST BE EXERCISED TO AVOID STRONG SOLVENTS OR HIGH TEMPERATURES WHEN USING THIS PIGMENT.

LIGHT RESISTANCE:

FULL SHADE VG TO EXC
TINT GOOD TO VG

SOLVENT RESISTANCE:

MINERAL SPIRITS FAIR
TOLUENE POOR
LACQUER POOR

PRODUCT CONSTANTS:

WEIGHT/GALLON 8.4 LBS.
PERCENT NVM 60.7%
PIGMENT YELLOW 65 40.0%
V.O.C./GALLON 3.3 LBS.

CHEMICAL RESISTANCE:

ACID VERY GOOD
ALKALI VERY GOOD

HEAT RESISTANCE: 280°F.

Date: 19 December 02