

PIGMENT PERFORMANCE DATA

PRODUCT NUMBER	PRODUCT NAME	COLOR INDEX NAME	LIGHT RESISTANCE		HEAT RESISTANCE 30 Min @ ° F	SOLVENT RESISTANCE				CHEMICAL RESISTANCE	
			Full Shade	Tint		Aliphatic	Aromatic	Ketone	Alcohol	Acid	Base
634-34130	Phthalo Blue RS	Blue 15:1	5	5	390	5	5	5	5	5	5
634-34860	Phthalo Green BS	Green 7	5	5	390	5	5	5	5	5	5
634-35430	Medium Yellow	Yellow 74	4-5	3-4	280	3-4	2-3	2-3	3-4	5	5
634-35660	Yellow RS	Yellow 65	4-5	3-4	280	2	1-2	1	2	5	5
634-35620	Yellow Oxide	Yellow 42	5	5	320	5	5	5	5	5	5
634-57560	Trans Yellow Oxide	Yellow 42	5	5	320	5	5	5	5	5	5
634-35940	Dinitraniline Orange	Orange 5	3	2	320	4	2	2	3	5	5
634-36560	Toluidine Red YS	Red 3	3-4	1-2	360	2-3	2	1-2	3	5	5
634-36570	Toluidine Red BS	Red 3	3-4	1-2	360	2-3	2	1-2	3	5	5
634-36770	Red Oxide	Red 101	5	5	>390	5	5	5	5	5	5
634-59278	Trans Red Oxide	Red 101	5	5	>390	5	5	5	5	5	5
634-37460	Carbazole Violet	Violet 23	4-5	3-4	320	5	4-5	4	5	5	5
634-39181	Carbon Black	Black 7	5	5	>390	5	5	5	5	5	5
634-39600	TiO ₂ White	White 6	5	5	>390	5	5	5	5	5	5
634-39660	Titanium Dioxide White	White 6	5	5	>390	5	5	5	5	5	5

Dated: 07 August 06
Supersedes: 08 May 06

LEGEND:

D – Darkens	3 – Good
5 – Excellent	2 – Fair
4 – Very Good	1 – Poor