

GIBRALTAR

See the Difference®

636

AEROCOAT DISPERSIONS

PIGMENT PERFORMANCE DATA

PRODUCT NUMBER	PRODUCT NAME	COLOR INDEX NAME	LIGHT RESISTANCE		HEAT RESISTANCE 30 Min @ ° F	SOLVENT RESISTANCE				CHEMICAL RESISTANCE	
			Full Shade	Tint		Aliphatic	Aromatic	Ketone	Alcohol	Acid	Base
636-34120	Phthalo Blue RS	Blue 15:1	5	5	390	5	5	5	5	5	5
636-34860	Phthalo Green BS	Green 7	5	5	390	5	5	5	5	5	5
636-35430	Medium Yellow	Yellow 74	4-5	3-4	280	3-4	2-3	2-3	3-4	5	5
636-35660	Yellow RS	Yellow 65	4-5	3-4	280	2	1-2	1	2	5	5
636-35770	Yellow Oxide	Yellow 42	5	5	320	5	5	5	5	5	5
636-35940	Dinitraniline Orange	Orange 5	3	2	320	4	2	2	3	5	5
636-35950	Bright Orange	Orange 34	3-4D	2	390	4-5	3	3-4	5	5	5
636-36560	Toluidine Red YS	Red 3	3-4	1-2	360	2-3	2	1-2	3	5	5
636-36570	Toluidine Red BS	Red 3	3-4	1-2	360	2-3	2-	1-2	3	5	5
636-36770	Red Oxide	Red 101	5	5	> 390	5	5	5	5	5	5
636-37110	Magenta	Red 122	4D	4-5	390	5	5	4-5	5	5	5
636-37430	Carbazole Violet	Violet 23	4-5	3-4	320	5	4-5	4	5	5	5
636-39190	Carbon Black	Black 7	5	5	> 390	5	5	5	5	5	5
636-39650	Titanium White	White 6	5	5	> 390	5	5	5	5	5	5

LEGEND:

D – Darkens
5 – Excellent
4 – Very Good

3 – Good
2 – Fair
1 – Poor

Dated: 07 August 2006
Supersedes: 09 May 2003