



## PRODUCT CONSTANTS

**955**  
UNIVERSAL DISPERSIONS

PRODUCT NUMBER	PRODUCT NAME	COLOR INDEX NAME	WEIGHT PERCENT			VOLUME PERCENT			WEIGHT/ GALLON	V.O.C. #/GAL
			Pigment	Vehicle Solids	Volatile	Pigment	Vehicle Solids	Volatile		
955-34120	Phthalo Blue RS	Blue 15:1	21.6	32.1	46.3	15.0	31.4	53.6	9.1	4.2
955-34250	Indanthrone Blue	Blue 60	27.5	26.8	45.7	20.0	27.0	53.0	9.3	4.2
955-34520	Phthalo Blue GS	Blue 15:3	29.2	27.4	43.4	21.0	27.1	51.9	9.4	4.1
955-34860	Phthalo Green BS	Green 7	28.0	26.1	45.9	15.6	27.8	56.6	9.8	4.5
955-35080	Chrome Oxide Green	Green 17	63.0	16.7	20.3	25.4	30.4	44.2	17.5	3.6
955-35160	Phthalo Green YS	Green 36	25.0	29.2	45.8	10.4	32.1	57.5	10.1	4.6
955-35410	Bright Yellow 151	Yellow 151	35.0	27.0	38.0	27.3	27.8	44.9	9.4	3.6
955-35440	Bright Yellow GS	Yellow 175	36.8	23.6	39.6	29.6	23.9	46.5	9.4	3.7
955-35470	Bright Yellow RS	Yellow 83	23.3	26.8	49.9	17.4	26.5	56.1	9.0	4.5
955-35560	Bright Yellow BV	Yellow 184	60.6	15.8	23.6	22.3	28.1	49.6	17.1	4.0
955-35330	Trans Yellow Oxide	Yellow 42	30.0	30.7	39.3	10.4	35.3	54.3	10.5	4.1
955-35670	Permanent Yellow RS	Yellow 110	40.0	26.4	33.6	27.2	29.2	43.6	10.2	3.4
955-35780	Yellow Oxide	Yellow 42	50.0	20.7	29.3	20.3	29.9	49.8	13.6	4.0
955-35920	Chroma Orange	NA	32.0	27.2	40.8	22.8	28.0	49.2	9.5	3.9
955-35930	Durable Orange	Orange 36	44.1	20.1	35.8	34.2	21.6	44.2	9.9	3.5
955-35950	Bright Orange	Orange 34	20.0	28.0	52.0	15.2	27.2	57.6	8.9	4.6
955-36500	Bright Red 170	Red 170	35.0	23.7	41.3	27.8	24.0	48.2	9.3	3.8
955-36530	Chroma Red	Red 254	35.7	29.3	35.0	26.3	31.0	42.7	9.7	3.4
955-36540	Deep Red 170	Red 170	25.6	27.1	47.3	21.0	26.2	52.8	8.9	4.2
955-36590	Perylene Red	Red 224	20.0	32.0	48.0	13.1	31.6	55.3	9.1	4.4
955-36640	Brilliant Red	NA	13.0	34.8	52.2	8.6	33.8	57.6	8.9	4.6
955-36420	Trans Red Oxide	Red 101	32.0	30.3	37.7	10.0	35.5	54.5	10.9	4.1
955-36760	Red Oxide	Red 101	65.9	18.2	15.9	29.4	34.2	36.2	18.2	2.9
955-37100	Quinacridone Violet	Violet 19	21.6	32.7	45.7	15.7	31.5	52.8	9.0	4.1
955-37200	Perylene Violet	Violet 29	22.0	31.2	46.8	14.0	31.3	54.7	9.3	4.3
955-37250	Perylene Maroon	Red 179	30.0	27.5	42.5	20.7	28.3	51.0	9.5	4.0
955-37470	Carbazole Violet	Violet 23	9.9	41.9	48.2	6.9	39.6	53.5	8.8	4.2
955-37500	Quinacridone Magenta	Red 122	20.0	33.2	46.8	15.1	31.8	53.1	8.9	4.2
955-39050	Conductive Black	Black 7	18.5	31.1	50.4	11.2	30.3	58.5	9.1	4.6
955-39230	Tinting Black	Black 7	34.0	28.2	37.8	22.6	29.9	47.5	9.9	3.7
955-39231	Shading Black	Black 7	20.8	43.5	35.7	13.0	44.9	42.2	9.4	3.4
955-39331	Jet Black	Black 7	11.8	41.7	46.5	7.4	38.9	53.7	8.7	4.0
955-39600	TiO <sub>2</sub> White	White 6	66.0	17.7	16.3	33.3	32.3	34.4	16.8	2.7